

## GREASE COMPATIBILITY CHART

	Aluminum Complex	Barium Complex	Calcium Stearate	Calcium 12-Hydroxy	Calcium Complex	Calcium Sulfonate Complex	Clay (Non-Soap)	Lithium Stearate	Lithium 12-Hydroxy	Lithium Complex	Polyurea (Conventional)	Polyurea Shear (Stable)
Aluminum Complex	-	I	I	C	I	B	I	I	I	B	I	C
Barium Complex	I	-	I	C	I	C	I	I	I	I	I	B
Calcium Stearate	I	I	-	C	I	C	C	C	B	C	I	C
Calcium 12-Hydroxy	C	C	C	-	B	B	C	C	C	C	I	C
Calcium Complex	I	I	I	B	-	I	I	I	I	C	C	C
Calcium Sulfonate Complex	B	C	C	B	I	-	I	B	B	C	I	C
Clay (Non-Soap)	I	I	C	C	I	I	-	I	I	I	I	B
Lithium Stearate	I	I	C	C	I	B	I	-	C	C	I	C
Lithium 12-Hydroxy	I	I	B	C	I	B	I	C	-	C	I	C
Lithium Complex	B	I	C	C	C	C	I	C	C	-	I	C
Polyurea (Conventional)	I	I	I	I	C	I	I	I	I	I	-	C
Polyurea (Shear Stable)	C	B	C	C	C	C	B	C	C	C	C	-

### Relative Compatibility Rating

**B = Borderline**

**C = Compatible**

**I = Incompatible**

NOTE: This chart is a general guide to compatibility. Specific properties of greases can dictate compatibility. Testing should be done to determine if greases are compatible.